

SONATE

Manufacturing process	Tufted	ISO 2424
Gauge	1/10" Loop	
Pilecomposition	100% PP	ISO 2424
Primary backing	Woven PP	ISO 2424
Secondary backing	Felt	ISO 2424
Width	400 cm ± 1%	EN 986
Pile weight	approx. 550 gr/m ²	ISO 8543
Total weight	Felt : approx. 1704 gr/m ² ± 15%	ISO 8543
Pile height	approx. 5,0 mm	ISO 1765
Total height	Felt : approx. 7,3 mm + 15% / -10%	ISO 1765
Number of knots	approx. 157.900 /m ² + 10% / -7,5%	ISO 1763
Fire classification	Felt : Efl (EN13501-1)	EN 13501-1
Light fastness	≥ 5	105-B02
Wearability	≥ 4,5	105-X12
Water fastness	≥ 4,5	105-E01
Thermal resistance	0,120 m ² K/W	ISO 8302
Sound insulation	10,0 dB	ISO 10140
GUT Nr.	Felt : D165EE7E	

Floorsymbols Felt



Certificates

