

STRONG

SEMI-COMMERCIAL FLOORING

Classification EN 685		42
Classification EN 685		33
Classification EN 685		23
Total thickness EN 428 (mm)*		2.4
Thickness of wear layer EN 429 (mm)*		0.60
Total weight EN 430 (g/m²)*		2100
Roll width EN 426 (m)		2/3/3.5/4
Roll length EN 426 (m)		18-27
Castor chair continuous use EN 425		✓
Light fastness EN ISO 105 B02		6/7
Thermal resistance ISO 8302 (m²K/W)		0.024
Reaction to fire EN 13501-1 (class)		B _{fl} / s1
Accoustical impact noise reduction EN ISO 140-8 (dB)		16
Resistance to household chemicals EN 423		Good
Elec. behaviour Body voltage EN 1815 (kV)		< 2.0
Elec. behaviour Vertical resistance EN 1081-A (Ω)		< 1*10 ⁹
Dynamic coefficient of friction Slip resistance EN 13893		> 0.7
Indentation-residual (mm) EN 433		≤ 0.15

* Tolerance of values ± 10%


** Follow Juteks installation and maintenance carefully on www.juteks.si



10
YEARS
guarantee

CE
EN 14041 : 2004

EMBOSSED
HIGH
DENSITY
BACKING





FRESKO 6063 2/3/3.5/4m



FRESKO 3062 2/3/3.5/4m



SCALA 7075 2/3/4m



SCALA 3275 2/3/3.5/4m



SCALA 2175 2/3/4m



SCALA 6275 2/3/3.5/4m



PARAISO 3057 2/3/4m



PARAISO 6057 2/3/4m



STEP 3181 2/3/4m



MARRON 3040 2/3/3.5/4m



CREON 1188 2/3/4m



CATAL 2041 2/3/4m



FALCO 7359 2/3/4m



ODINA 1323 2/3/4m