


Zenith PD

Manufacturing process	Needlefelt		ISO 2424
Surface aspect	Velour		ISO 2424
Width	200 cm, 400 cm		
Backing	PD		ISO 2424
Fibre composition	75% PP / 25% PES		
Total fibre weight of use surface	420 gr/m ²		
Total weight	1650 gr/m ²	+/- 15%	ISO 8543
Pile height	3,0 mm		ISO 1766
Total height	5,8 mm	+15% / -10%	ISO 1765
Flammability	Cfl,s1 (Glued)		EN 13501-1

Floorsymbols



Certificates



ISO 9001:2015-certified processes
ISO 14001:2015-certified processes

2023-11-23