

RIFF

SWING COLLECTION

CONSTRUCTION STRUCTURE STRUKTUR STRUCTUUR	Tufting 1/10" scroll Tufté 1/10" scroll Getuftet 1/10" scroll Getuft 1/10" scroll	FASTNESS TO LIGHT SOLIDITÉ A LA LUMIÈRE LICHTECHTHEIT LICHTECHTHEID	EN ISO 105-B02 ≥ 5-6
PILE MATERIAL COMPOSITION DU VELOURS POLMATERIAL POOLMATERIAAL	100% PA	COLOUR FASTNESS TO WATER SOLIDITÉ À L'EAU WASSERECHTHEIT WATERECHTHEID	EN ISO 105-E01 ≥ 4-5
SECONDARY BACKING DOSSIER RÜCKEN TAPIJTRUG	Texflor® back	FIRE RESISTANCE COMPORTEMENT AU FEU BRENNVERHALTEN BRANDGEDRAG	EN 13501-1 E _{FL} -s1
PILE WEIGHT POIDS DU VELOURS POLEINSATZGEWICHT POOLGEWICHT	± 295 gr/m ²	WIDTH LARGEUR BREITE BREEDTE	EN ISO 3018 ca. 400, 500 cm
TOTAL WEIGHT POIDS TOTAL GESAMTGEWICHT TOTAAL GEWICHT	± 1.300 gr/m ²	DESIGN REPEAT CM RACCORD CM RAPPORT CM DESSINRAPPORT CM	ca 30 (W) x 93 (H)
PILE THICKNESS EPAISSEUR DU VELOURS POLDICKE POOLDIKTE	± 3 mm		
TOTAL THICKNESS EPAISSEUR TOTALE GESAMTDICKE TOTALE DIKTE	± 5 mm		
TUFT DENSITY NOMBRE DE POINTS NOPPENZAHL AANTAL PUNTEN	± 169.000/m ²		
PRODIS / GUT	TBC		
CLASSIFICATION CLASSEMENT KLASSIFIKATION CLASSIFICATIE	EN 1307 22 - LC1		



ITC CO BV
Kanegemstraat 15, B-8700 Tielt
itc-carpets.com

EN 14041
CE
25
ITC CO BV Kanegemstraat 15 - BE 8700 Tielt
DOP: 1011#IE00EL
Textile Floor Covering EN1307
    
my.itc-carpets.com