

## Betap

De Blokmat 29 8281 JH  
Genemuiden, The Netherlands  
T +31 (0)38 386 10 60  
E centralmail@betap.com  
W www.condor-group.eu

# Sun Felt

## Technical specifications

Manufacturing process	Needlefelt		ISO 2424
Width	200 cm, 400 cm		
Backing	Felt		ISO 2424
Fibre composition	100% PES		
Total weight	740 gr/m <sup>2</sup>	+/- 15%	ISO 8543
Basis weight of pile	240 gr/m <sup>2</sup>	+/- 15%	ISO 984
Pile height	2.0 mm		ISO 1766
Total height	3.5 mm	+15% / -10%	ISO 1765
Flammability	Efl		EN 13501-1

