

Lugano Felt

Betap

De Blokmat 29 8281 JH
Genemuiden, The Netherlands
T +31 (0)38 386 10 60
E centralmail@betap.com
W www.condor-group.eu

Technical specifications

Tuft gauge	1/10 cut pile	ISO 2424
Pilecomposition	100% PP	ISO 2424
Primary Backing	Woven	ISO 2424
Secondary backing	Felt	ISO 2424
Width	400 cm	± 1% EN 984
Pile Weight	1.275 gr/m ²	ISO 8543
Total weight	Felt : 2.070 gr/m ²	± 15% ISO 8543
Pile height	12.0 mm	± 10% ISO 1766
Total Height	Felt : 13.5 mm	ISO 1765
Number of knots	78.750 /m ²	-7.5% .+10% ISO 1763
Fire Classification	Efl	EN 13501-1
Use Area	Medium domestic use (22)	EN 1307



 Betap Tufting B.V. De Blokmat 29 8281 JH Genemuiden EN1307 DOP: 101649300 Reaction to fire: Efl Slip resistance: > 0.3 Felt Resilient floor covering to be used within a building on the floor	 Betap Tufting B.V. De Blokmat 29 8281 JH Genemuiden EN1307 DOP: 101649300-UK Reaction to fire: Efl Slip resistance: > 0.3 Felt Resilient floor covering to be used within a building on the floor
--	---